



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁷ : C08L 101/14, C09D 133/02, D06M 15/263 // (C09D 133/02, 133:26, 175:04)	A1	(11) International Publication Number: WO 00/29486 (43) International Publication Date: 25 May 2000 (25.05.00)
(21) International Application Number: PCT/US99/25660 (22) International Filing Date: 3 November 1999 (03.11.99) (30) Priority Data: 09/190,866 13 November 1998 (13.11.98) US (71) Applicant (for all designated States except US): OWENS CORNING [US/US]; One Owens Corning Parkway, Toledo, OH 43659 (US). (72) Inventors; and (75) Inventors/Applicants (for US only): FLAUTT, Martin, C. [US/US]; 230 Knoll Drive, Granville, OH 43023 (US). PRIEST, James, R. [US/US]; 7285 Cedar Court East, Nashport, OH 43830 (US). STOTLER, David, V. [US/US]; 1158 Sharon Valley Road, Newark, OH 43055 (US). HAGER, Thomas, P. [US/US]; 1109 Lake Point Drive, Westerville, OH 43082 (US). (74) Agents: ECKERT, Inger, H. et al.; Owens Corning Science & Technology Center, 2790 Columbus Road, Building 54-1, Granville, OH 43023-1200 (US).		(81) Designated States: AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, DE, DK, DM, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i>
(54) Title: SUPERABSORBENT WATER-RESISTANT COATINGS FOR FIBER-REINFORCED ARTICLES (57) Abstract <p>A coating composition for forming a water-resistant coating on fiber-reinforced articles such as rods or cables. The composition comprises an aqueous solution of a superabsorbent water-soluble polymer, a viscosity modifying agent, and optionally a lubricant. The coating formed by applying the composition effectively prevents the treated surface from water-permeation damage by absorbing water that contacts the layer containing the superabsorbent component.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon			PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

SUPERABSORBENT WATER-RESISTANT COATINGS
FOR FIBER-REINFORCED ARTICLES

Technical Field and Industrial Applicability of the Invention

5 The present invention relates to a high strength superabsorbent coating capable of rapidly absorbing water, which is suitable for coating reinforcing fibers, or for coating articles comprising reinforcing fibers, such as reinforced rods and cables. More specifically, the coating is formed from a composition comprising a superabsorbent polymer precursor which, upon cure, forms a polymer with a high water swelling ability;
10 and a film-forming polymer. As a modification to adapt the coating to pultruded articles, the coating composition may also include a viscosity-modifying agent.

 The inventive concept also relates to articles coated with the superabsorbent coating composition, such as glass rods; and methods of applying such coatings. The novel coating of this invention demonstrates a high level of water absorption in fresh and
15 salt-water environments, and excellent spreading and coating ability when applied to a substrate.

Background of the Invention

 Deterioration caused by the invasion of moisture beneath the exposed surfaces of
20 articles used in outdoor environments is a well-known problem. This deterioration includes oxidative deterioration caused by reaction of water with the surfaces of reinforcing fibers used in these articles, as well as water-induced corrosion. In marine environments, the problems associated with waterlogging are particularly compounded by the salinity of the environment. The presence of salt in such aqueous environments
25 hastens the oxidative decomposition.

 Articles affected by the deterioration described above include reinforced fibers made of glass, carbon, polymer or mixtures thereof, or items containing such reinforcing fibers. The term "articles", as used herein, is specifically intended to include reinforcing fiber materials known in the art, as well as products made using one or more of these
30 fibers collectively or dispersed within a matrix of any type. The term also includes articles manufactured using reinforced fiber products, such as structural materials or in equipment. Examples of such articles include such as reinforced rods and cables, such as fiber optic or telecommunications cables. These telecommunications cables are often

used in situations where they are buried underground or submerged in water over long periods. As such, protection from water damage is critical to the structural integrity of these cables and to the success of the functions they are intended to perform. A telecommunications cable, for example, may include a core comprising a glass rod that
5 acts as a stiffening or reinforcing member. This rod contributes to the rigidity of the cable. When water penetrates to contact the core element of the cable, corrosion or chemical deterioration of the cable infrastructure may result.

In order to combat the problems associated with this waterlogging damage, several strategies have been devised in an attempt to provide water resistance to cables and other
10 reinforced articles, and to protect their sensitive inner surfaces from contact with water or water vapor present in the surrounding environment. These techniques for making water-repellent articles have included wrapping the articles in a protective sheathing material; or sealing the surface to be protected. Sealing techniques may include chemically manipulating the surface layer of the article to render it resistant to water-absorption, or
15 applying a repellent coating.

The technique of covering the surface with a protective sheathing material is conventional. It includes for example, using a wrap or tape made of an impervious polymer with water-blocking ability, or treating the wrapping material with an emulsion or solution of a water-blocking polymer. The sheathing process does not require
20 application of a chemical compound or treatment to the surface of the article, rather the protection is derived only from the coverage by the sheathing material.

Coatings used to repel water traditionally have been composed of substances that are both insoluble and impenetrable to water, and therefore presented a physical barrier to encroaching moisture. Such barrier coatings have included materials such as greases or
25 gels. In the case of cables, for example, these coatings are applied by extrusion under pressure. There are however, certain drawbacks associated with this type of coating. Greases or gels are difficult to handle because of their slipperiness, and they contribute an unpleasant feel to the coated article. This is an important factor to be considered in the manufacturing process, particularly because it affects the ease of handling of the cable
30 during splicing operations. Greases and gels also undergo changes in viscosity at low or high temperatures. These viscosity changes may affect the freeze/thaw performance and therefore the stability of the coating. Poor performance in these respects therefore affects the stable performance of the cables.

More recently, greaseless, water-resistant dry coatings have been devised which, of themselves, have some degree of water-absorbing capacity. This ability to absorb water allows the coating to absorb the moisture contacting the article, while preventing direct contact with the sensitive surfaces. The absorbent component in these dry

5 waterblocking coatings is a dry, granulated superabsorbent polymer that swells and absorbs upon contact with water. The superabsorbent polymers are usually characterized in terms of their swell rate, swell capacity and gel strength. Traditional uses for these dry superabsorbent polymers have primarily included personal hygiene product articles, food packaging articles and chemical spill cleanup compositions, however recent

10 experimentation has included using these dry polymers to form coatings for other articles such as reinforced cables. For example, US 5,689,601 to Hager, herein incorporated by reference, discloses a dry waterblocking coating for reinforcing fiber articles using a powdered or granulated water-soluble dry blocking ingredient encased in one or more thin layers of a sheathing polymer. This casing restricts the degree of water absorption that

15 can be achieved by the granular polymer, and accordingly the swell capacity of this coating is limited.

The superabsorbent polymers traditionally used in dry waterblocking cable coating applications are dry, granular polymers that are incorporated into various substrates such as yarn, binders and tape. The substrates typically also contain glass fibers as a form of

20 reinforcement. However, as discussed above, the coatings formed with dry granulated blocking agents suffer the limitations of limited water swelling ability and swell rate as a necessary consequence of optimizing the gel strength. In the context of surface coatings, gel strength is defined as the ability to prevent water from wicking down the cable axis, particularly when the cables are used in aqueous environments where they are exposed to

25 elevated water pressures. The swelling ability is directly related to the degree of cross-linking of the superabsorbent polymer. As the degree of cross-linking increases, so does the gel strength, but there is a related decrease in the swell rate and swell capacity of the polymer. The swell rate defines the amount of water that the coating absorbs over a fixed period of time. The swell capacity denotes the maximum amount of water or fluid

30 absorbed by the coating, based on a measure of its dry weight. Consequently, coatings made of dry, granular, water-insoluble polymer are limited in their water-absorbing performance, as measured in terms of the swell rate and swell capacity.

Generally, coatings for reinforced fibers, strands and articles such as cables that

are made from these fibrous materials are applied to the surface of the fibrous material and then cured before further processing, if any, occurs. The means of applying coatings, in general, differs depending on whether a fluid coating is used or whether a solid particulate coating is being applied.

5 In the case of powdered coatings, the coating process using granulated water-blocking agents involves several time-consuming and labor- and equipment-intensive steps that are directly related to the use of a granulated polymer. These steps include the need for one or more treatments with a binding resin, and one or more applications of powdered resin at the powder-coating stations using apparatus such as a fluidized bed.

10 The means for applying fluid coatings may include flooding, or dipping the fibers or cables, for example, in a resin bath and then removing excess resin and form a consistent layer on the treated surface. In the case of strands, rovings or cables, the product is in the form of a continuous filament and therefore it can be passed through a stripper die to remove the excess resin. Alternatively, the coating may be sprayed onto
15 the surface of the article. In order to form a coating layer that is thick enough to provide good coverage and protection from water penetration, the coating composition must be thick enough that it can adequately coat the article in one pass through the coating apparatus. In addition to thickness however, the composition must also have sufficient flowing ability to allow ready formation of a uniform coating on the surface of the article,
20 and to prevent clogging of the coating apparatus, dye orifices or other machinery used to make polymer-coated fibrous articles. Traditionally in the art, in order to modify the viscosity of the fluid coating composition, dry particulate ingredients such as a flocculent polymer or starch have been used. The difficulty with such compositions is that the resulting composition after this solid ingredient is added is not homogenous. Rather, the
25 composition contains varying levels of a particulate material, which makes handling difficult and also compromises the spreadability of the composition.

 There exists in the art then, a need for a waterblocking coating composition which possesses excellent gel strength and wicking ability, as well as a high degree of water absorption and a concurrent, rapid swell rate. At the same time, a further need exists in
30 the art for a coating composition that does not contain powdered polymer, and which, as a result, would not require a costly and labor intensive application process. At the same time it is desired that such a coating composition exhibit good spreading and surface performance characteristics.

SUMMARY OF THE INVENTION

It has now surprisingly been discovered that highly absorbent waterblocking coatings having an excellent water swelling capacity and a rapid swell rate can be formed by incorporating a solution of a superabsorbent polymer precursor into an aqueous solution used to coat glass fiber reinforced articles such as cables or rods. The polymer precursor, when cured, forms a superabsorbent polymer. The novel coatings containing this superabsorbent polymer are capable of substantially instantaneous water absorption when exposed to aqueous environments.

Depending on the intended application, the absorbent coating may be enhanced by adding a viscosity-modifying agent. For example, where the coating composition is applied to rods comprising glass, carbon, polymer or mixtures thereof, including a viscosifier imparts excellent spreading ability to the formulation. This viscosity-modifying agent is not an insoluble powdered component, rather it is a polymeric solution or dispersion that can be easily incorporated into the coating composition. Hence, unlike waterblocking coatings previously known in the art, the coating composition of this invention is in the form of a true solution having substantially no particulate components.

In one aspect, this invention also relates to a process of forming a coating onto fibers or strands of a reinforcing material. The process of coating may further be applied to products containing reinforced fiber materials, such as rods or cables formed from a composite making process such as pultrusion or injection molding. Generally, this process includes the steps of applying the coating composition to the surface of the fibers, strands or articles, passing it through a stripper die to remove excess coating, followed by a drying or curing step.

The inventive concept further relates to articles containing reinforcing fibers made of glass, polymer, carbon or natural fibers that are made using the water-absorbent coatings of the present invention. Such articles include reinforcing fibers, strands, rods, rovings etc., either in continuous form or as chopped fibers, strands, or pellets; fabrics comprised of glass, polymer or natural fibers; and pultruded articles such as rods or cables. The pultruded articles may be comprised of glass, carbon, one or more polymers, and mixtures thereof. Also, the coating can be applied to corrugated metallic tubes and tapes used for rodent protection in fiber optic cables.

DETAILED DESCRIPTION OF THE PREFERRED
EMBODIMENTS OF THE INVENTION

The composition of this invention is suitable for forming a superabsorbent coating on the surface of fiber reinforcements and fibrous products or articles made using these reinforcements. The products to which the composition may be applied can be divided into the broad categories of fiber reinforcements, such as continuous strands, or composited articles comprising fiber reinforcements and one or more other components. The ingredients included in the superabsorbent coating formulation depend on the type of product to which the composition will be applied.

As one embodiment, examples of fibrous reinforcement products in the first category mentioned above include strands or rovings made from fiber-forming materials such as glass, carbon, polymers or mixtures thereof. The coating formulation for these products will preferably include a small amount of a lubricant.

In another embodiment, the composited articles in the second category include articles that comprise a reinforcing fiber material as at least one component thereof. Examples include articles formed in a pultrusion operation. For example, the coatings of this invention can be successfully applied to a pultruded rod or cable comprised at least partially of reinforcing glass fiber/polymer composite. The polymers that may be used to form these pultruded articles include thermosetting resins, such as epoxies, polyesters and vinyl esters. The polymer component of the pultruded article may also be a thermoplastic resin that has been heat-treated, however a thermosetting resin is preferred. As an example, a thermosetting epoxy resin such as a vinyl ester may be combined with glass strands in a pultrusion operation to form a rod that can be used as the stiffening member in a telecommunications cable.

The water resistant properties of the coatings of the present invention are obtained by combining a solution of a non-toxic, environmentally safe superabsorbent polymer precursor with the binder resin used to coat the substrate articles. The superabsorbent polymer formed by this precursor possesses a surprisingly high capacity for absorbing water, and at the same time maintains a high gel strength in the cured coating as a result of increased cross-linking. As mentioned previously, this polymer uniquely provides water resistance by absorbing large quantities of water. As water contacts the coated surface of the article to be protected, the coating absorbs water and swells in volume. By absorbing the water, the coating effectively wicks away the moisture and thus prevents it

from contacting the inner surfaces of the protected article. As a result, the sensitive inner surfaces remain dry and are protected from waterlogging deterioration. The coatings of this invention uniquely achieve water resistance protection by absorbing water to prevent moisture penetration beneath the coating layer. This function is distinctly different from the type of protection accomplished by the barrier coatings more commonly known in the art, which protect the substrate by forming an impermeable barrier.

The non-toxic, environmentally safe superabsorbent polymer precursor used in the coatings of this invention may be selected from any such polymer capable of forming an aqueous solution for use in the coating mixture, and which, upon cure, has a swell capacity and swell rate that enables rapid absorption of large amounts of water followed by desorption without loss of the polymer itself when the coating is dried. A polymer precursor suitable for use in the present coating will demonstrate a swell capacity of up to about 400 times its initial dry weight when the coating is applied to reinforcing fibers or strands and cured.

The superabsorbent polymer precursor for use in the present invention may, for example, be selected from the group of water-soluble polyacrylates possessing the required ability to absorb and desorb large quantities of water, as has been previously mentioned. The superabsorbent polymer precursor is preferably used in its anionic form as a salt of a corresponding alkali or alkali metal salt. The polymer salt is in the form of an aqueous solution that is either clear or slightly cloudy in appearance. A desirable solids content is in the range of from 30-35% weight. The solution also has a specific gravity of about 1.1 grams per milliliter and a viscosity of about 1000 mPas at about 20°C. The solution is typically slightly anionic, having a pH of from about 6 to about 8. One example of an acceptable superabsorbent polymer precursor is a water-soluble anionic polyacrylate in aqueous solution.

If the coating is to be applied to pultruded articles, a viscosity-modifying agent may also be added to the coating composition. The role of this viscosifier is to create a spreading consistency that will enable adequate coating of the pultruded article after it has been passed through a stripper die. The viscosifier also provides good flowing ability and prevents clogging of the coating apparatus and die orifices. Viscosity modifying agents capable of forming a true solution, such as alkyl cellulose or acrylamide polymers, may be used in the coatings of this invention. A preferred viscosifier for use in the present coatings is a polyacrylamide in aqueous solution. The polyacrylamide solution is

particularly suitable because of its compatibility with the superabsorbent polymer precursor solution and the film-forming binder component.

The binder component used in the coating compositions of this invention can include any polymeric material customarily used as a binder in coating compositions for reinforced fiber-containing products. The binder preferably comprises a film-forming polymer or polymer latex that is a thermosetting resin or a thermosetting resin with some thermoplastic properties to enhance the flexibility of the coating. The film-forming binder is also necessarily compatible with the water-absorbing polymer and with the viscosity-modifying agent, in that it promotes combination of the ingredients in the coating composition, and also facilitates adherence of the coating to the surface once it is applied. The film-former further provides a tough film with preferably no surface tackiness or flaking of the coating after it is cured. The film-forming polymer comprised in the binder may for example be a polyester, urethane, epoxy, latex or mixtures thereof. The latex may in turn be selected from an acrylic latex, a styrene-butadiene latex, or mixtures thereof. Preferably, the binder is a film-forming urethane that promotes adherence of the water-absorbing polymer to the treated surface after it is dried. An example of a desirable film-forming binder is Witcobond W320, which is a polyurethane film-former available from Witco Chemical Co.

Optionally, the coating composition may also include one or more additives selected from the group consisting of lubricants and wetting agents. Lubricants are added to enhance the handling of the polymer-impregnated strand in subsequent processing. Where the coating is applied to fiber reinforcements such as glass strands, a lubricant is preferably added to improve adherence of the coating to the strand.

The wetting agent is added to facilitate contact between the dispersion and the fiber surface. Any conventional wetting agent that is compatible with the other ingredients of the sizing composition can be used.

When the coatings of the invention are applied to the surfaces of reinforcing fiber strands and cured, they demonstrate a swell capacity of from about up to about 400 times the initial dry weight of the water-swellaable polymer. Preferably, the swell capacity for this type of application is from about 200 to about 400 times the initial dry weight of the water-swellaable polymer. Where the coatings are applied and cured on the surface of articles such as rods or cables, the swell capacity ranges up to 120 times the initial dry

weight of the water-swellaable polymer. In this context, preferably the swell capacity is from about 50 to about 100 times the initial dry weight of the water-swellaable polymer.

The swell rate of the coating should also be high. The coatings of this invention demonstrate an exceptionally high swell rate, in the order of from about 300% to about 2000% weight in the first minute, based on the total weight of the polymer and the fiber substrate. The rate of water uptake varies depending on the salinity of the aqueous environment in which the coating is used. In fresh water, the swell rate is higher than can be achieved in a saline solution such as a marine environment. However, whether the coating is used in either a fresh or salt-water environment, its performance, as measured by the swell rate, is demonstrably higher than has been previously achieved by dry waterblocking coatings known in the art.

In the method of making the coating compositions of this invention, the ingredients are combined in liquid form to prepare the coating solution. A solution of the superabsorbent polymer precursor is first stirred to ensure homogeneity, then added to a mixing tank. Deionized water is then added to the tank, and the lubricant, if desired, is then introduced. Next, the polyurethane in the form of an aqueous emulsion is pumped into the tank. The viscosity-modifying agent is first premixed to form a 1 % aqueous solution, and a sufficient amount of this aqueous solution is added to the mixing tank. As a final step, the mixture is then stirred, without heating, and the resulting composition is ready for application.

The composition is contacted with the surface of the articles to be coated by a means suitable for applying a liquid coating. For example, the coating composition can be applied by passing reinforcing fiber strands through a resin bath. Alternatively, the composition is applied to an article to be coated by spraying, flooding, or by any other means which permits the liquid coating to be contacted with the entire surface of the article. A further processing means may then be used to ensure an even and adequate distribution of the coating layer. For example, fiber strands or rods coated with the coating composition are passed through a stripper die.

The coated articles are then dried and cured. The article coated with the superabsorbent polymer precursor is heated to 212°F for a period sufficient to volatilize a substantial portion of the water. The polymer precursor-coated article is then heated to approximately 280 °F to cure the polymer by cross-linking. Typically, polymers heated to above approximately 300 °F lose the desired superabsorbent quality. The drying/curing

step may be performed in an in-line oven. In a 25 foot long oven set to approximately 600 °F the polymer is cured at 380-490 feet per minute, and preferably at 440-465 feet per minute.

5 Glass fiber reinforced articles having the water resistant coating herein described may be used in applications where exposure to water or water vapor is likely, and where the formation of a durable, resilient, flexible coating with good waterproofing properties is desired. The following examples are representative, but are in no way limiting as to the scope of this invention.

10 EXAMPLES

Exemplary coating formulations were prepared by combining a film-forming binder polymer, a water-absorbing polymer precursor solution and a polyacrylamide solution. The coating compositions were then applied to pultruded glass-vinyl ester rods using a flooding process. After the coating composition was applied, the rod was passed
15 through a stripper of desired orifice size to control the amount of coating composition deposited on the surface of the rod. The rod was then heated to volatilize the water component, then further heated to about 270°F to cure the coating and activate the superabsorbent polymer precursor.

20 Example 1

In this example, a coating composition for treating pultruded glass/polymer rods was formulated by mixing the ingredients in the proportions listed below:

- 33.3 % weight of a superabsorbent polyacrylate precursor solution (aqueous),
available commercially as Stockhausen 63815 from Stockhausen Inc.;
- 25 25.0 % weight of a urethane film-forming polymer, Witcobond W290H, available
from Witco Chemical Co.; and
- 41.7 % weight of a 1 % aqueous acrylamide solution, Drewfloc 270, which is
available commercially from Ashland Chemical Inc.

30 Example 2

In this coating composition for pultruded rods, the ingredients were combined as follows:

- 28.6 % weight Stockhausen 63815 superabsorbent polyacrylate precursor solution;

35.7 % weight urethane film-forming polymer, Witcobond W320, available from Witco Chemical Co.; and

35.7 % weight of a 1 % aqueous solution of Drewfloc 270.

5 Example 3 - Water Resistance Testing

 An exemplary coating composition was developed according to the following formulation:

 40.0 % weight Stockhausen 63815 superabsorbent polyacrylate precursor solution;

 7.5 % weight Witcobond W320polyurethane film-forming polymer;

10 2.0 % weight Emerlube 7440, a sulfonated mineral oil available from Henkel Corp.;

 2.0 % weight of a 1 % aqueous solution of Drewfloc 270; and

 48.5 % weight of deionized water.

 The composition was applied to glass fiber reinforcement strands designed for use in
15 optical cables. The reinforcements were then immersed in either deionized water or in a
1% saline solution. The swell rate in both the fresh water and the marine environments
were determined by measuring the percentage swell or increase in weight over time
intervals ranging from 0-20 minutes. As a comparison, strands coated with a dry
waterblocking coating using granulated polymer powder were also immersed in both the
20 fresh and salt-water environments for the same period of time.

 The strands coated according to this invention and immersed in deionized or fresh
water showed a swell rate that was up to seven times faster than the swell rate for the rods
coated with the dry, granulated polymer, within the first minute of exposure. The swell
capacity or the overall amount of swell was up to 270% higher in comparison to the dry
25 coating. In the salt-water environment, the coating of this invention demonstrated a swell
rate that was more than 6 times faster than the dry granulated coating within the first
minute of exposure. The coating also showed up to 50% more swell capacity than the dry
coating.

 These results clearly show that the coating solutions of the present invention
30 achieve superior water absorption, and correspondingly, superior water resistance, when
they are applied to articles that are exposed over prolonged periods to an aqueous fresh- or
salt-water environment.

Examples 4-5

The coatings of the present invention were further investigated to determine their efficacy when applied to reinforcing fiber materials such as strands or rovings. Strands of glass reinforcing fibers were coated with the invention and the percentage swell over time, calculated based on the total weight of coating and fiber was measured. In comparison, strands coated with the dry, granular coatings were also tested to determine the swell rate of the coating. In Example 4, the reinforcements were immersed in deionized water. For Example 5, the reinforcements were exposed to a 1% sodium chloride solution. The results obtained are included in Table 1 and 2 below:

Table 1

Example 4 – Water Absorption in Deionized Water

Time (minutes)	Swell Rate ^a (% swell / time)	
	Example 4	Comparison Sample
0	0	0
0.033	612	86
0.0833	677	119
0.1666	730	168
0.25	nr ¹	210
0.333333	745	nr
0.5	751	264
0.666666	754	nr
0.83333	758	nr
1	762	336
1.5	770	nr
2	778	nr
5	810	480
10	865	575
20	975	650

¹nr = not recorded^a Swell rate was measured as the percentage change in weight of the coated strand per unit time.

5

Table 2

10 Example 5 – Water Absorption in 1% Sodium Chloride Solution

Time (minutes)	Swell Rate ^a (% swell / time)	
	Example 5	Comparison Sample
0	0	0
0.030	225	38
0.0833	237	47
0.25	265	81
0.5	276	88
1	295	99
2	312	118
5	325	140
10	350	142
20	415	158

It is believed that Applicants' invention includes many other embodiments which are not herein specifically described, accordingly this disclosure should not be read as being limited to the foregoing examples or preferred embodiments.

WHAT IS CLAIMED IS:

1. A coating composition for an article comprising a superabsorbent water-soluble polymer precursor in aqueous solution.
- 5 2. The coating composition of claim 1, wherein the superabsorbent water-soluble polymer precursor is a polyacrylate.
3. The coating composition of claim 1, further comprising a viscosity-modifying agent.
4. The coating composition of claim 3, wherein the viscosity-modifying agent is an aqueous solution of a polymeric material selected from the group consisting of
10 polyacrylamides.
5. The coating composition of claim 1, further comprising a lubricant.
6. The coating composition of claim 1, further comprising a binder.
7. The coating composition of claim 6, wherein the binder is a polyurethane.
8. A coating formed on the surfaces of a reinforcing article, comprising a
15 superabsorbent water-soluble polymer.
9. The coating of claim 8, wherein the superabsorbent water-soluble polymer, after curing, absorbs up to about 400 times its initial dry weight in water when immersed in an aqueous environment, and desorbs water when the coating is dried.
- 20 10. The coating of claim 8, further comprising a viscosity-modifying agent.
11. The coating of claim 8, further comprising a lubricant.
12. The coating of claim 11, wherein the article comprising a reinforcing fiber material is a fiber strand selected from the group consisting of glass, carbon, one or more polymers, natural fibers and mixtures.
- 25 13. The coating of claim 12, having a swell rate of from about 300 % to about 2000 % weight, based on the total weight of coated strand, in the first minute.
14. An article having a coating comprising:
a superabsorbent polymer;
a viscosity modifying agent; and
30 a binder.
15. A method of forming a superabsorbent, water-resistant coating on the surface of an article comprising:

- a) preparing a liquid coating composition comprising a superabsorbent water-soluble polymer precursor that absorbs and desorbs water when the coating is exposed to an aqueous or moisture-containing environment and a viscosity modifying agent;
 - 5 b) applying the liquid coating composition to the surface of the article to form a water-absorbing, water-resistant coating layer on the surface of the article; wherein said article comprises reinforcing fibers; and
 - c) drying and curing the liquid coating to form a water-absorbing, water-resistant coating layer on the surface of the article.
- 10 16. The method of claim 15, wherein the step of applying the liquid coating composition to the surface of the article comprises contacting the liquid coating composition with the surface of the article to form a layer of liquid coating over the entire surface of the article.
- 15 17. An aqueous coating composition comprising:
a superabsorbent polymer precursor;
a viscosity-modifying agent; and
a binder.
- 20 18. The aqueous coating composition of claim 17, wherein the superabsorbent polymer precursor is selected from the group consisting of anionic alkali salts and alkali metal salts of said superabsorbent polymer.
19. The aqueous coating composition of claim 17, wherein the superabsorbent polymer precursor is a polyacrylate.
20. The aqueous coating composition of claim 17, wherein the viscosity-modifying agent is selected from the group consisting of alkyl celluloses, acrylamide
25 polymers and mixtures thereof.
21. The aqueous coating composition of claim 20, wherein the viscosity-modifying agent is a polyacrylamide.
22. The aqueous coating composition of claim 17, wherein the binder is selected from the group consisting of polyesters, polyurethanes, epoxies, latex and mixtures
30 thereof.
23. The aqueous coating composition of claim 22, wherein the binder is a film-forming polyurethane.
24. The coated article of claim 14, wherein the article is fiber containing.

25. The coated article of claim 14, wherein the article is a fiber.
26. The coated article of claim 14, wherein the article is a bundle of fibers.

INTERNATIONAL SEARCH REPORT

Int'l Application No
PCT/US 99/25660

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 C08L101/14 C09D133/02 D06M15/263 //(C09D133/02,133:26, 175:04)

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C08L C09D D06M

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
P,X	WO 99 10591 A (WILLEMSSEN STEPHANUS ;AKZO NOBEL NV (NL)) 4 March 1999 (1999-03-04) claims 1-5 examples 1,2	1-4,6,8,9
X	WO 96 23024 A (WILLINK BLYDENSTEIN NV ;KROESBERGEN AALBERTUS PIETER (NL)) 1 August 1996 (1996-08-01) claims 1-4,10,13,15-17 page 2, line 30 - line 37 page 5, line 29 - line 38 page 7, line 26 -page 8, line 11 example 1	1-3,6-8,10,14-19,22-26
X	US 5 071 681 A (MANNING JAMES H ET AL) 10 December 1991 (1991-12-10) claims 1,5	1,2,8
	-/-	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document relating to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- "&" document member of the same patent family

Date of the actual completion of the international search

24 February 2000

Date of mailing of the international search report

06/03/2000

Name and mailing address of the ISA

European Patent Office, P.B. 6818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax (+31-70) 340-3016

Authorized officer

Hallemeesch, A

INTERNATIONAL SEARCH REPORT

International Application No
PCT/US 99/25660

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 5 236 982 A (PIRET WILLY ET AL) 17 August 1993 (1993-08-17) claims 1,13,14,22 column 5, line 50 - line 68	1,2,5-8, 11,12
X	US 4 214 531 A (CZEREPIŃSKI RALPH G ET AL) 29 July 1980 (1980-07-29) claim 1	1-4

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 99/25660

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 9910591 A	04-03-1999	AU 9261698 A	16-03-1999
WO 9623024 A	01-08-1996	NL 1000572 C	23-07-1996
		AU 4678996 A	14-08-1996
		BR 9606835 A	30-12-1997
		CA 2211111 A	01-08-1996
		CN 1176650 A	18-03-1998
		EP 0813566 A	29-12-1997
		FI 973018 A	18-09-1997
		HU 9801765 A	30-11-1998
		JP 10513123 T	15-12-1996
		PL 321462 A	08-12-1997
		US 5998312 A	07-12-1999
US 5071681 A	10-12-1991	EP 0357474 A	07-03-1990
US 5236982 A	17-08-1993	DE 69306746 D	30-01-1997
		DE 69306746 T	12-06-1997
		EP 0603376 A	29-06-1994
		ES 2098047 T	16-04-1997
		HK 1008013 A	30-04-1999
		JP 6511227 T	15-12-1994
		WO 9401375 A	20-01-1994
US 4214531 A	29-07-1980	US 4186250 A	29-01-1980
		AU 1218476 A	22-09-1977
		BE 840390 A	05-10-1976
		CA 1070876 A	29-01-1980
		DE 2615075 A	21-10-1976
		FR 2306832 A	05-11-1976
		GB 1495895 A	21-12-1977
		JP 51122501 A	26-10-1976
		NL 7603530 A	11-10-1976
		US 4266481 A	12-05-1980
		US 4200688 A	29-04-1980